

DESY-Bibliothek

3. JKT. 1969

Interner Bericht  
DESY F41-69/3  
September 1969

Optical Properties and Electronic Density of States

Manuel Cardona

Brown University, Providence, Rhode Island

and

Deutsches Elektronen-Synchrotron DESY, Hamburg, Germany

Paper to be presented at the NBS-Symposium "Electronic Density of States"  
Nov.3.-6.,1969 in Washington, D.C.



OPTICAL PROPERTIES AND ELECTRONIC DENSITY  
OF STATES<sup>†</sup>

Manuel Cardona<sup>†</sup>

Brown University, Providence, Rhode Island

and

DESY, Hamburg, Germany

The fundamental absorption spectrum of a solid yields information about critical points in the optical density of states. This information can be used to adjust parameters of the band structure. Once the adjusted band structure is known, the optical properties and the density of states can be generated by numerical integration. We review in this paper the parametrization techniques used for obtaining band structures suitable for density of states calculations. The calculated optical constants are compared with experimental results. The energy derivative of these optical constants is discussed in connection with results of modulated reflectance measurements. It is also shown that information about density of empty states can be obtained from optical experiments involving excitation from deep core levels to the conduction band.

A detailed comparison of the calculated one-electron optical line shapes with experiment reveals deviations which can be interpreted as exciton effects. The accumulating experimental evidence pointing in this direction is reviewed together with the existing theory of these effects.

A number of simple models for the complicated interband density of states of an insulator have been proposed. We review in particular the Penn model, which can be used to account for response functions at zero frequency, and the parabolic model, which can be used to account for the dispersion of response functions in the immediate vicinity of the fundamental absorption edge.

# Supported by the National Science Foundation and the Army Research Office, Durham.

+ John Simon Guggenheim Foundation Fellow.

## 1. Optical Properties and One-Electron Density of States

The optical behavior of semiconductors and insulators in the near infrared, visible, and ultraviolet is determined by electronic interband transitions. An additional intraband or free electron contribution to the optical properties has to be considered for metals. We shall discuss here the relationship between the interband contribution and the density of states. The interband contribution to the imaginary part of the dielectric constant can be written as (in atomic units,  $\hbar = 1$ ,  $m = 1$ ,  $e = 1$ ):

$$\epsilon_i(\omega) = \frac{1}{4\pi\omega} \iint_{\omega_{ef}=\omega} \frac{\underline{F}^{ef}}{|\nabla_{\underline{k}} \omega_{ef}|} dS_{\underline{k}} \quad (1)$$

where  $\omega_{ef} = \omega_e - \omega_f$  is the difference in energy between the empty bands (e) and the filled bands (f). The spin multiplicity must be included explicitly in Eq. (1). The oscillator strength tensor  $\underline{F}^{ef}$  is related to the matrix elements of  $\underline{p}$  through  $\underline{F}^{ef} = 2 \langle f | \underline{p} | e \rangle \langle e | \underline{p} | f \rangle \omega_{ef}^{-1}$ . The Bloch functions are normalized over unitvolume. Degenerate statistics has been assumed in Eq. (1) and spatial dispersion effects have been neglected.

It is customary to take the slowly varying oscillator strength out of the integral sign in Eq. (1) and thus write:

$$\epsilon_i(\omega) = \frac{2\pi^2}{\omega} \bar{F} N_d(\omega) \quad (2)$$

where  $\bar{F}$  is an average oscillator strength and  $N_d$  the combined optical density of states.

Structure in  $\epsilon_1(\omega)$  (Eq. (1)) appears in the neighborhood of critical points, where  $\nabla_{\underline{k}} \omega_{ef} = 0$ . Such critical points can be localized in a small region of  $\underline{k}$  space or can extend over large portions of the Brillouin zone over which filled and empty bands are parallel (sometimes only nearly parallel). Once the critical points which correspond to observed optical structure are identified in terms of the band structure through various devious and sometimes dubious arguments, their energies can be used to adjust parameters of semiempirical band structure calculations.

Four different parametric techniques of calculating band structures have been used for this purpose: the empirical pseudopotential method (EPM)<sup>1</sup> the  $\underline{k}\cdot\underline{p}$  method<sup>2</sup> the Fourier expansion technique (FE)<sup>3</sup> and the adjustable orthogonalized plane waves method (AOPW)<sup>4</sup>.

Once reasonably reliable band structures are known it is important to calculate from them the imaginary part of the dielectric constant  $\epsilon_1(\omega)$  and to compare it with experimental results so as to confirm or disprove the initial tentative assignment of critical points and thus the accuracy of the band structures. Rich structure is obtained in both, experimental and calculated spectra and hence a rather stringent test of the accuracy of the available theoretical band structure is in principle possible.

In order to calculate numerically the integral of Eq.(1) it is necessary to sample eigenvalues and eigenfunctions at a large number of points in the Brillouin zone. The amount of computer time required for solving the band structure problem with first-principles methods (OPW, APW, KKR) at a general point of the Brillouin zone makes such methods impractical for evaluating Eq. (1). The parametric methods (EPM,  $k \cdot p$ , FE, but not AOPW) require only the diagonalization of a small matrix (typically  $30 \times 30$ ) and hence it is possible to sample the band structure at about 1000 points with only a few hours of computer time. Cubic materials, in particular those with  $T_d$ ,  $O$ , and  $O_h$  point groups, are simple in this respect: symmetry reduces the sampling required for the evaluation of Eq. (1) to only  $1/48$  of the Brillouin zone. Hexagonal and tetragonal materials have relatively larger irreducible zones and hence a larger number of sampling points is necessary if the resolution of the calculation is not to suffer. Once the band structure problem has been solved for all points of a reasonably tight regular mesh, the bands and matrix elements at arbitrary points can be obtained by means of linear or quadratic interpolation.

The method of Gilat and coworkers<sup>5</sup> has become rather popular for the numerical evaluation of Eq. (1)<sup>4,6</sup>. In the case of a cubic material the Brillouin zone is divided into a cubic mesh and the band structure problem solved at the center of these cubes (sometimes a finer mesh is generated by quadratic interpolation from the coarser mesh<sup>6</sup>). Within each cube of the mesh

the bands are linearly interpolated and approximated by their tangent planes. The areas of constant energy plane within each cube corresponding to a given  $\omega_{ef}$  are added after multiplying them by the corresponding oscillator strength and thus the integral of Eq. (1) is obtained.

The real part of the dielectric constant  $\underline{\epsilon}_r$  can be obtained from  $\underline{\epsilon}_i$  by using the Kramers-Kronig relations. It is also possible to obtain  $\underline{\epsilon}_r$  and  $\underline{\epsilon}_i$  simultaneously by calculating the integral:

$$\underline{\epsilon}(\omega) = 1 - \frac{1}{2\pi^2} \iiint \frac{\underline{F}^{ef} \omega_{ef}}{[\omega_{ef}^2 - (\omega + i\eta)^2]} dV_{\underline{k}} \quad (3)$$

with  $\eta$  small and positive. For  $\eta \rightarrow +0$  the imaginary part of Eq. (3) coincides with Eq. 1. Equation (3) can be evaluated with a Monte Carlo technique. Points are generated at random in  $\underline{k}$  space within the Brillouin zone and the average value of the integrand for these points calculated. The process can be interrupted when reasonable convergence as a function of the number of random points is achieved.<sup>7,8</sup>

We show in Fig. 1 the results of a calculation of  $\epsilon_i$  from the  $\underline{k} \cdot \underline{p}$  band structure of InAs with the method of Gilat and Raubheimer.<sup>6</sup> The band structure problem, including spin-orbit effects, was solved at about 150 points of the reduced zone (1/48 of the BZ). We have indicated in this figure the symmetry of the critical points (or of the approximate regions of space)



where the structure in  $\epsilon_1$  originates. The experimental  $\epsilon_1$  spectrum, as obtained from the Kramers-Kronig analysis of the normal incidence reflectivity<sup>9</sup>, is also shown. The agreement between calculated and experimental spectra is good, with regards to both position and strength of the observed structure, with the exception of the position of the  $E_2$  peak. This is to be attributed to an improper assignment of the  $E_2$  peak when the 6 adjustable band structure parameters were determined. The  $E_2$  peak had been attributed, following the tradition, to an X critical point while it is actually due to an extended region of  $k$  space centered around the U points.<sup>8</sup> It should be a simple matter to readjust the band structure parameters to lower the energy of the calculated  $E_2$  peak by about 0.5 eV; in view of the large amount of computer time required to recalculate the energy bands this has not been done. The structure calculated around 6 eV, due mostly to spin-orbit splitting of the  $L_3$  levels, has not yet been observed experimentally.

The conventional experimental determination of  $\epsilon_1$  from normal incidence reflection data<sup>9</sup> suffers from considerable inaccuracy: To the experimental error produced by possible improper surface treatment and contamination one has to add the uncertainty in the high-energy extrapolation of the experimental data required for the Kramers-Kronig analysis. Some of these difficulties are avoided by comparing the calculated reflectivity spectra (obtained from  $\epsilon$  with Fresnel's equation) with the experimental results. This is done in Fig. 2 for GaSb: the experimental data<sup>10</sup> have not been Kramers-Kronig analyzed because of the

small range of the energy scale. Two calculated spectra have been plotted in this figure: one obtained from the  $\underline{k}\cdot\underline{p}$  band structure<sup>6</sup> and the other obtained from a non-local pseudo-potential calculation with 14 adjustable parameters.<sup>11</sup> The discrepancy between experimental and calculated curves at high energy, a common feature of many zincblende-type materials<sup>12</sup>, has two origins: the measured reflectivity should be low because of increased diffuse reflectance at small wavelengths while the calculated one should be high because of the finite number of bands included in the calculation. In this region where  $\epsilon_r - 1$  is small, the contribution to  $\epsilon_r$  of transitions not included should lower the calculated reflectivity.

During the past few years a lot of activity has been devoted to the measurement and analysis of differential reflection spectra obtained with modulation techniques.<sup>13-15</sup> The wavelength (or photon energy) derivative spectra<sup>14</sup> should permit an accurate analysis of the line shapes of the spectra of Figs. 1 and 2. We show in Fig. 3 the temperature modulated reflection spectrum (thermoreflectance) of GaSb<sup>15</sup>: it has been shown that for the III-V materials<sup>15</sup> this spectrum is very similar to the photon energy derivative spectrum, difficult to obtain experimentally. The corresponding photon energy derivative spectrum obtained from the calculation of Fig. 2 is also shown in Fig. 3. The calculated and experimental shapes of the  $E_1$ ,  $E_1 + \Delta_1$  peaks show discrepancies of the type attributed in Sec. 2 to exciton interaction. Derivative spectra for other germanium and zincblende

type materials have been calculated by Walter and Cohen<sup>12</sup> and by Higginbotham<sup>16</sup>.

The methods to calculate band structures from first principles, without or with only a few adjustable parameters (one<sup>17</sup> or three<sup>4</sup>) have recently achieved considerable success. However the calculation of energy bands at one general point of the BZ requires a lot of time so as to make density of states calculations prohibitive. Moreover, the evaluation of the matrix elements required for Eq. 1 is difficult with first principles techniques. It is nevertheless possible to use first principles calculations at a few high-symmetry points of the Brillouin zone to adjust the parameters of semiempirical band structures from which the large number of sampling points required for the evaluation of Eq. 1 can be obtained with relative ease. The  $\underline{k}\cdot\underline{p}$  technique has proved particularly useful in this respect<sup>1,18,19</sup> Matrix elements of  $\underline{p}$  can be easily evaluated from the eigenvectors in the  $\underline{k}\cdot\underline{p}$  representation. Spin-orbit interaction can also be easily included. This  $\underline{k}\cdot\underline{p}$  procedure has been applied to the relativistic OPW band structure calculated by Herman and Van Dyke for gray tin<sup>19</sup>. Figure 5 shows the reflectivity of gray tin calculated by this procedure with the method of Gilat and Raubenheimer together with experimental results.<sup>20</sup> Comparison with other experimental results for the germanium family suggests that the high-energy end of the measured spectrum is too low, probably due to surface imperfections in the delicate crystals, grown from mercury solution, which were used for this experiment.

The  $k \cdot p$  fitting procedure has also been applied to a first principles relativistic APW calculation of the band structure of PbTe by Buss and Parada<sup>7</sup>. Figure 6 shows the reflectivity of PbTe obtained by this method with a Monte Carlo sampling technique and Fig. 7 the absorption coefficient, both compared with experimental data<sup>7,21,22</sup>. In both cases the semiquantitative agreement between experimental and calculated data is remarkably good in view of the absence of adjustable parameters. The calculated reflectivity is, at high energies, considerably higher than the experimental one, as discussed earlier for other materials. The  $E_1$  peak of the experimental reflectivity spectrum appears split in the calculated spectrum, possibly because of inaccuracies in the first principles band structure. The calculated  $E_1$  structure appears due mostly to transitions along the  $\Sigma$  direction. The experimental  $E_1$  structure has been assigned<sup>23</sup> to the lowest gap along  $\Sigma$ . The calculated  $E_2$  peak corresponds to an extended region of the BZ without definite symmetry, as inferred from electroreference measurements<sup>23</sup>.

We have so far discussed optical constants for cubic materials. While calculations for materials with lower symmetry require more computer time, one has the extra reward of being able to predict the experimentally observed anisotropy. Figure 7 shows the two principal components of  $\epsilon_1$  for trigonal Se as calculated by Sandroek<sup>24</sup> from the pseudopotential band structure. The similarity between calculated and experimental results, also shown in Fig. 7<sup>25</sup>, is especially remarkable in view of the method used to determine the pseudopotential parameters:

They were determined from the pseudopotential parameters required to fit the optical structure of ZnSe. Only a small adjustment was performed so as to bring the calculated fundamental gap (1.4 eV) into agreement with the experimental one (2.0 eV). The dielectric constant of antimony (trigonal) for the ordinary and the extraordinary ray has also been calculated by a similar procedure.<sup>26</sup>

The reasonable agreement obtained between experimental and calculated optical constants suggests the use of the corresponding band structure to determine the individual density of states  $D(\omega)$ : The main work, that of diagonalizing the Hamiltonian at a large number of points, has already been done. The programs required to calculate individual density of states are very similar to those used for the evaluation of Eq. (1):  $\omega_{ef}$  must be replaced by the single band energies and  $F^{ef}$  must be removed. As an example we show in Fig. 8 the individual density of states of the 3 highest valence bands (six including spin) and the 3 lowest conduction bands of gray tin.<sup>19</sup> Direct information about the individual density of states can be obtained by a number of methods discussed in this conference. We mention, in particular, optical techniques involving transitions from deep core levels to the conduction band or from the valence band to temporarily empty core levels (soft X-ray emission).<sup>27</sup> If the sometimes questionable assumption of constant matrix elements is made, the corresponding spectra represent the conduction (for absorption spectra) and the valence (for emission spectra) density of states because of the small width of the core bands. We show in Fig. 9 the

density of states of the conduction band of Ge calculate by Herman et al.<sup>4</sup> and the corresponding density of states for GaSb as obtained by the  $\underline{k}\cdot\underline{p}$  method.<sup>6</sup> The density of states for both materials are very similar because of the similarity of their band structures. We also shown in Fig. 9 the quantity  $\epsilon_1 \omega^2$  obtained by Feuerbacher et al.<sup>28</sup> for Ge in the region of the  $M_{4,5}$  edge. The origin of energies has been shifted so as to make a comparison with the conduction density of states possible:  $\epsilon_1 \omega^2$  should be proportional to  $D(\omega)$  under the assumption of constant matrix elements of  $\underline{p}$ . While the rich structure of the calculated density of states is not seen in the  $\epsilon_1 \omega^2$  curve, this curve is reproduced quite well if the density of states is broadened so as to remove the fine structure. The required lifetime broadening of about 1 eV is not unreasonable for the  $M_{4,5}$  transitions. Using Eq. (2) with  $N_d$  replaced by the conduction density of states we obtain an average oscillator strength at the maximum of  $\epsilon_1 \omega^2$   $\bar{F} = 0.15$ . This oscillator strength corresponds to the 20 4d electrons per unit cell and hence it should be divided by 20 to obtain the average oscillator strength per d-band. If one reasons that the transitions from 10 of the 20 d bands to a given conduction band are forbidden because of the spin flip involved while transitions from 5 of these 10 bands are forbidden or nearly forbidden by parity, one finds for the average oscillator strength of each one of the 5 allowed bands  $\bar{F} = 0.03$ , which corresponds to a matrix element of  $\underline{p} = 0.13$  (in atomic units): this value is quite reasonable in view of the fact that the typical valence-conduction matrix element is 0.6.

The small value of this matrix element explains why the d core electrons are negligible in the  $\underline{k}\cdot\underline{p}$  analysis of the valence and conduction masses.

## 2. Exciton Effects

We have devoted Sec. 1 to a comparison of experimental optical spectra with calculations based on the one-electron band structure. Exciton effects, i.e. the final state Coulomb interaction between the excited electron and the hole left behind, are known to modify substantially the fundamental edge of semiconductors and insulators.<sup>29</sup> Exciton modified interband spectra seem also to occur in metals at interband edges which have the final state on the Fermi surface.<sup>30</sup> Experimental evidence for these effects is reported at this conference in the paper by Haensel et al.

We shall now discuss the question of exciton effects above the fundamental edge of insulators and semiconductors with special emphasis on the zincblende family. As mentioned in Sec. 1 the gross features of these spectra are explained by the one-electron theory. The exciton interaction is responsible, at most, for small details concerning the observed line shapes. It is generally accepted<sup>31,32</sup> that the exciton interaction suppresses structure in the neighborhood of  $M_3$  critical points: the Coulomb attraction with negative reduced masses is equivalent to a repulsion with positive masses. Such a repulsion smoothes out critical point structure: no  $M_3$  critical point has been conclusively identified in the experimental spectra. The  $E_1$  and  $E_1+\Delta_1$  critical points of

figures 1-3 are of the  $M_1$  variety. Hence the line shape of the corresponding  $\epsilon_1$  spectrum should be characterized by a steep low-energy side and a broader high-energy side. Figure 10 shows the shape of the  $E_1$  peak observed at low temperature by Marple and Ehrenreich<sup>33</sup> and by Cardona<sup>34</sup>. In order to avoid effects due to the overlap of the  $E_1$  and the  $E_1 + \Delta_1$  peaks it has been assumed that they have exactly the same shape but shifted by 0.55 eV. The contribution of only  $E_1$  has been extracted from the measured  $\epsilon_1$  spectrum and displayed in Fig. 10. It is clear from this figure that the  $E_1$  peak is steeper at high energies than at low energies, against the expectations for an  $M_1$  peak. Also in Fig. 10 we show the results of a calculation by Kane<sup>32</sup> of the effect of Coulomb interaction on the  $E_1$  line shape for CdTe, using the effective mass approximation. The solution of effective mass Hamiltonian with non-positive-definite mass is made easier by the fact that the negative mass (along the  $\Lambda$  direction) has a magnitude much larger (about ten times) than the two equal positive masses. It is possible to use the adiabatic approximation<sup>31</sup>, i.e., to solve the two-dimensional hydrogen atom problem with the third coordinate as a parameter and then solve the adiabatic equation for the third coordinate. The agreement between the calculated and the experimental line shapes of Fig. 10 is excellent.

Attempts have been made to calculate the dielectric constant including exciton interactions at an arbitrary point of  $\underline{k}$  space, independently of the stringent restrictions of the effective mass approximation.<sup>35,36</sup> Such calculation is possible if one truncates the Coulomb interaction between electron and hole Wannier packets



to extend to a finite number of neighboring cells. The extreme and simplest case of a  $\delta$ -function (Koster-Slater) interaction can be solved by hand<sup>31,35</sup> and gives around an  $M_1$  critical point the shapes of  $\epsilon_r$  and  $\epsilon_i$  shown in Fig. 11: For an  $M_1$  critical point the Koster-Slater interaction mixes the  $M_1$  one-electron line shape with the  $M_{1+1}$ . The high energy side of the  $\epsilon_i$  peak becomes steeper, in agreement with Fig. 10. The line shape observed for the  $E_1-E_1+\Delta_1$  peaks in the reflectivity spectrum is composed almost additively of the  $\epsilon_i$  and  $\epsilon_r$  line shape: at the energies of these peaks  $dR/d\epsilon_i$  and  $dR/d\epsilon_r$  are almost equal. We also show in Fig. 11 the line shapes expected for the reflectivity spectra of the  $E_1-E_1+\Delta_1$  peaks and for the corresponding differential spectra ( $dR/d\omega$ ). We show in Fig. 12 the photon energy derivative spectrum of these peaks in HgTe<sup>37</sup>: the observed line shapes disagree with those expected from the one-electron theory (equal positive and negative peaks) but agree with those predicted in the presence of a Koster-Slater interaction (Fig. 11). Similar results have been found for other zincblende-type materials.<sup>37</sup>

### 3. Simplified Models for the Density of States

As seen in Sec. 1 the optical density of states, and thus the dielectric constant, is a complicated function of frequency and its calculation requires lengthy numerical computation. For some purposes, however, it can be approximated by simple functions. In the vicinity of a critical point of the  $M_1$  variety, for instance, the dielectric constant can be approximated

by:

$$E \propto i^{r+1} (\omega - \omega_g)^{1/2} + \text{constant} \quad (4)$$

if exciton effects are neglected. Exciton interaction can be included, within the Koster-Slater model, by adding to  $\pm$  a positive number smaller than one.

As shown in Fig. 1,  $\epsilon_1$  for the zincblende-type materials has a strong peak ( $E_2$ ) in the neighborhood of which most of the optical density of states is concentrated. The corresponding transitions occur over a large region of the BZ, close to its boundaries. In order to represent this fact, Penn<sup>38</sup> suggested the model of a non-physical spherical BZ with an isotropic gap at its boundaries. The complex energy bands of the material are then replaced by those of a free electron with an isotropic gap  $\omega_g$  at the boundary of a spherical BZ. This gap should occur in the vicinity of the  $E_2$  optical structure. While this model represents rather poorly the rich structure of  $\epsilon_1$  (Fig. 1), it is expected that it should give a good picture of  $\epsilon_r$  at zero frequency. The reshuffling of density of states involved in the case of the isotropic model should not affect  $\epsilon_r(\omega=0)$  very much because of the large energy denominators which appear in Eq. (3) for  $\omega=0$ : the lowest gap  $\omega_0$ , usually much smaller than  $\omega_g$ , accounts only for a very small fraction of the optical density of states. Penn obtained with this model the static dielectric constant for a finite wavevector  $q$ . The result can be approximated by the analytic expression:<sup>38</sup>

$$\epsilon(\omega=0, \underline{q}) = 1 + \left( \frac{\omega_p}{\omega_g} \right)^2 \mathcal{F} \left\{ 1 + \frac{\omega_F}{\omega_g} \frac{q}{k_F} \mathcal{F}^{1/2} \right\}^{-2} \quad (5)$$

$$\text{with } \mathcal{F} = 1 - \frac{\omega_g}{4\omega_F} + \frac{1}{3} \left( \frac{\omega_g}{\omega_F} \right)^2$$

In Eq. (5)  $\omega_p$  is the plasma frequency obtained for the density of valence electrons and  $\omega_F$  and  $k_F$  the corresponding free electron Fermi energy and wave number. The dimensionless quantity  $\mathcal{F}$  is usually close to one.

Figure 13 shows Eq. (5) for Si compared with the exact results of the Penn model.<sup>39</sup> These results are obviously independent of the direction of  $\underline{q}$ . A small dependence on this direction is found from a complete pseudopotential calculation by Nara<sup>40</sup> (see also Fig. 13). The function  $\epsilon(0, \underline{q})$  is of interest for the treatment of dielectric screening.

Equation (5) yields for  $\underline{q}=0$  the electronic contribution to the static dielectric constant:

$$\epsilon_0 = 1 + \mathcal{F} \left( \frac{\omega_p}{\omega_g} \right)^2 \approx 1 + \left( \frac{\omega_p}{\omega_g} \right)^2 \quad (6)$$

The experimental values of  $\epsilon_0$  agree reasonably well with the results of Eq. (6) using for  $\omega_g$  the energy of the  $E_2$  peak.<sup>34</sup> Equation 6 has gained recent interest as the basis of Phillips and Van Vechten's theory of covalent bonding.<sup>41, 42, 43</sup> These authors use Eq.(6) and the experimental values of  $\epsilon_0$  to define

the average gap  $\omega_g$ . With this gap and the corresponding gap of the isoelectronic group IV material they can interpret a wide range of properties such as crystal structure<sup>42</sup>, binding energy,<sup>43</sup> energies of interband critical points,<sup>41</sup> non-linear susceptibilities<sup>44</sup>, etc. As an example we discuss the hydrostatic pressure (i.e. volume) dependence of  $\epsilon_0$  for germanium and silicon. According to Van Vechten<sup>41</sup>,  $\omega_g$  for C, Ge, Si, and  $\alpha$ -Sn is proportional to  $(a_0)^{-2.5}$  where  $a_0$  is the lattice constant. If one makes the assumption that this law gives also the change in  $\omega_g$  with lattice constant for a given material when hydrostatic stress is applied one can calculate the volume dependence of  $\epsilon_0$ .<sup>41</sup> Neglecting the one in Eq. (6), a valid approximation for Ge and Si, one finds:

$$\frac{1}{\epsilon_0} \frac{d\epsilon_0}{dV} = 2 \left( \frac{d \ln \omega_g}{dV} - \frac{d \ln \omega_g}{dV} \right) = 2 [0.83 - 0.50] = 0.66 \quad (7)$$

Equation (7) explains the sign and the small magnitude observed for  $(1/\epsilon_0)(d\epsilon_0/dV)$ . The experimental values of this quantity are 1.0 for Ge and 0.6 for Si.<sup>41,45</sup>

According to Eq. (6) the average gap  $\omega_g$  determines the electronic dielectric constant for  $\omega=0$ . As the lowest gap  $\omega_0$  is approached ( $\omega_0 \ll \omega_g$  usually),  $\epsilon_r$  exhibits strong dispersion. This dispersion is due, in the spirit of Eq. (3), to the density of states in the vicinity of  $\omega_0$ . For the purpose of calculating the dispersion of  $\epsilon_r$  immediately below  $\omega_0$ , the density of states can be approximated by that of parabolic bands with a reduced mass equal to the reduced mass  $\mu$  at  $\omega_0$ . These bands are assumed to extend to infinity in  $k$  space: the unphysical contribution

to  $\epsilon_r$  for  $|k| \rightarrow \infty$  should be small for  $\omega \leq \omega_0$ , because of the large energy denominators of Eq. (3). We thus obtain for a cubic material the following contribution of the  $\omega_0$  gap to the scalar dielectric constant below  $\omega_0$  (under the assumption of an constant matrix element of  $\underline{p}$  equal to  $\underline{P}$ ):<sup>46</sup>

$$\Delta \epsilon_r = 2 (2\mu)^{3/2} \omega_0^{3/2} |P|^2 f(\omega/\omega_0) = C_0'' f(\omega/\omega_0) \quad (8)$$

with  $f(x) = 2 - (1+x)^{1/2} - (1-x)^{1/2}$ .

Equation (8) represents quite well the behavior of  $\epsilon_r$  immediately below  $\omega_0$  for the lead chalcogenides<sup>47</sup> and a number of other semiconductors<sup>48</sup>. As an example we show in Fig. 14 the observed dispersion of  $\epsilon_r$  below  $\omega_0$  at room temperature<sup>49</sup> together with a fit based on Eq. (8).<sup>48</sup> For the sake of completeness we have included in the fitting equations not only the effect of  $\omega_0$  ( $E_0$ ) but also that of its spin-orbit-split mate  $E_0 + \Delta_0$  (also represented by an expression similar to Eq. 8), the dispersion due to the  $E_1$  and  $E_1 + \Delta_1$  gaps, and that due to the main  $\omega_g$  gap assuming  $\omega_g \cong E_2$ . Thus the fitting equation, with three adjustable parameters  $C_0''$ ,  $C_1''$ ,  $C_2''$  is: <sup>48</sup>

$$\epsilon_r(\omega) = 1 + C_0'' \left\{ f(x_0) + \frac{1}{2} \left( \frac{\omega_0}{\omega_{cs}} \right)^{3/2} f(x_{cs}) \right\} + C_1'' \left\{ h(x_1) + \left( \frac{\omega_1}{\omega_{1s}} \right) h(x_{1s}) \right\} + C_2'' (1 + 2x_2^2) \quad (9)$$

where:

$$\omega_{cs} = \omega_0 + \Delta_0, \quad x_{cs} = \frac{\omega}{\omega_{cs}}, \quad x_1 = \frac{\omega}{\omega_1}$$

$$\omega_{1s} = \omega_1 + \Delta_1, \quad x_{1s} = \frac{\omega}{\omega_{1s}}, \quad x_2 = \frac{\omega}{\omega_g}$$

$$h(x_1) = 1 + \frac{x_1^2}{2}$$

The fitting values of  $C_0''$  (6.602) and  $C_1''$  (2.791) are in qualitative agreement with those calculated from the band parameters.<sup>48</sup>

The parabolic model density of states can also be used to interpret the strong dispersion in the piezobirefringence observed near the lowest direct gap of Ge, GaAs,<sup>48</sup> and other III-V semiconductors:<sup>50,51</sup> uniaxial stress splits the top valence band state ( $\Gamma_8$ ) and a birefringence in the contribution of  $E_0$  to  $\epsilon_r'$  results because of the selection rules for transitions from the split bands. The main contribution to this piezobirefringence is expected to be proportional to  $f'(x)$ , which diverges like  $(\omega - \omega_0)^{-1/2}$  for  $\omega \rightarrow \omega_0$ . Such behavior can be seen in the experimental results (circles) of Fig. 15 obtained for GaAs at room temperature. Included in this figure is the corresponding fit based on the model of Eq. (9).<sup>48</sup>

The long wavelength, non-dispersive contribution to the piezobirefringence of Fig. 15 can be interpreted, at least qualitatively, in terms of the Penn model of Eqs. (6) and (7). Equation (7) yields two contribution to the change in  $\epsilon_r$  one due to the change in plasma frequency (i.e. carrier density) with stress and the other due to the change in the isotropic gap. The first contribution should not exist for a pure shear stress. For a hydrostatic stress the second contribution can be written in tensor form as:

$$\frac{1}{\epsilon_0} \Delta \epsilon_{mm} = 5 e_{mm} \quad (10)$$

where  $\underline{e}$  is the strain tensor. We postulate that Eq. (8) remains valid for pure shear stress. This crude generalation has a clear physical meaning in terms of the Penn model. The spherical BZ becomes ellipsoidal under a shear stress and the energy gap at an arbitrary point of the BZ boundary  $k_F$  becomes anisotropic. The gap at  $k_F$  is assumed to become larger as  $k_F$  becomes larger ( $k_F$  is the distance between atomic planes perpendicular to  $k_F$ ). Equation 8 gives the right sign for the long wavelength contribution to the piezobirefringence of Fig. 15 but a magnitude about five times larger. The agreement becomes better if the contribution of the  $E_0$  edge to the long wavelength piezobirefringence, of opposite sign to that predicted by Eq. 8<sup>48</sup>, is subtracted from the experimental results.

I am indebted to Drs. Buss, Kane, Phillips, and Van Vechten for sending preprints of their work, prior to publication and to the staff of DESY for their hospitality.

1. M.L. Cohen and T.K. Bergstresser, Phys.Rev. 141, 789 (1966)
2. M. Cardona and F.H. Pollak, Phys.Rev. 142, 530 (1966)
3. G. Dresselhaus and M.S. Dresselhaus, Phys.Rev. 160, 649 (1967)
4. F. Herman, R.L. Kortum, C.D. Kuglin, and J.L. Shay, in "II-VI Semiconducting Compunds" ed. by D.G. Thomas (W.A. Benjamin, New York, 1967) p. 503
5. G. Gilat and G. Dolling, Phys.Letters 8, 304 (1964)  
G. Gilat and L.J. Raubenheimer, Phys.Rev. 144, 390 (1966)
6. C.W. Higginbotham, F.H. Pollak, and M. Cardona, Proceedings of the IX International Conference on the Physics of Semiconductors, Moscow 1968 (Publishing House Nauka, Leningrad, 1968) p. 57
7. D. Buss and N.J. Parada, Phys.Rev., in Press
8. E.O. Kane, Phys.Rev. 146, 558 (1966)
9. H.R. Philipp and H. Ehrenreich, Phys.Rev. 129, 1550 (1963)
10. M. Cardona, Z. Physik 161, 99 (1961)
11. H.I. Zhang and J. Callaway, Phys.Rev. 181, 1163 (1969)
12. J.P. Walter and M.L. Cohen, Phys.Rev., to be published
13. B.O. Seraphin and N. Bottka, Phys.Rev. 145, 628 (1966)
14. K.L. Shaklee, J.E. Rowe, and M. Cardona, Phys.Rev. 174, 828 (1968)
15. E. Matatagui, A.G. Thompson, and M. Cardona, Phys.Rev. 176, 950 (1968)
16. C.W. Higginbotham, Ph.D. Thesis, Brown University, 1969
17. P. Eckelt, O. Madelung, and J. Treusch, Phys.Rev. Letters 18, 656 (1967)



18. W. Brinkman and B. Goodman, Phys.Rev. 149, 597 (1966)
19. F.H. Pollak, M. Cardona, C.W. Higginbotham, F. Herman, and J.P. Van Dyke, Phys.Rev., to be published
20. P. McElroy, Ph.D. Thesis, Harvard University, 1968
21. M. Cardona and D.L. Greenaway, Phys.Rev. 133, A 1685 (1964)
22. W.W. Scanlon, J.Phys.Chem.Solids 8, 423 (1959)
23. D.E. Aspnes and M. Cardona, Phys.Rev. 173, 714 (1968)
24. R. Sandrock, Phys.Rev. 169, 642 (1968)
25. S. Tutihasi and I. Chen, Phys.Rev. 158 623 (1967)
26. P.J. Lin and J.C. Phillips, Phys.Rev. 147, 469 (1966)
27. G. Wiech, in "Soft X-Ray Spectra" ed. by D.J. Fabian, (Academic Press, New York, 1968) p. 59
28. B. Feuerbacher, M. Skibowski, R.P. Godwin, and T. Sasaki, JOSA 58, 1434 (1968)
29. See for instance R.S. Knox, "Theory of Excitons", (Academic Press, N.Y., 1963)
30. G.D. Mahan, Phys.Rev. Letters 18, 448 (1967)
31. B. Velický and J. Sak, Phys. Status Solidi 16, 147 (1966)
32. E.O. Kane, Phys.Rev. 180, 852 (1969)
33. D.T.F. Marple and H. Ehrenreich, Phys.Rev. Letters 8, 87 (1962)
34. M. Cardona, J.Appl.Phys. 36, 2181 (1965)
35. M. Inoue, M. Okazaki, Y. Toyozawa, T. Inui, and E. Nanamura, Proc.Phys.Soc. Japan 21, 1850 (1966)
36. J. Hermanson, Phys.Rev. 150, 660 (1966)
37. K.L. Shaklee, Ph.D. Thesis, Brown University, 1969
38. D. Penn, Phys.Rev. 128, 2093 (1962)

39. G. Srinivasan, Phys.Rev. 178, 1244 (1969)
40. H. Nara, J.Phys.Soc. Japan 20, 778 (1965)
41. J.A. Van Vechten, Phys.Rev., in Press (2 articles)  
In this reference a correction factor of the order of unity is added to Eq. 6 so as to take the polarizability of the core d electrons into account
42. J.C. Phillips, Phys.Rev. Letters 20, 550 (1968)
43. J.C. Phillips, Covalent Bonding in Molecules and Solids (University of Chicago Press, Chicago) to be published.
44. J.C. Phillips and J.A. Van Vechten, to be published.  
B.F. Levine, Phys.Rev. Letters 22, 787 (1968)
45. M. Cardona, W. Paul, and H. Brooks, J.Phys.Chem.Solids 8, 204 (1959)
46. L.I. Korovin, Soviet Phys.Solid State 1, 1202 (1959)
47. M. Cardona in "High Energy Physics, Nuclear Physics, and Solid State Physics". edited by I. Saavedra (W.A. Benjamin, New York, 1968)
48. C.W. Higginbotham, M. Cardona, and F.H. Pollak, Phys.Rev., inpress.
49. W.M. De Meis, Technical Report No. HP-15 (ARPA-16), Harvard University (1965)
50. A. Yu. Shileika, M. Cardona, and F.H. Pollak, Solid State Communications, in Press
51. P.Y. Yu, to be published.

1. Imaginary part of the dielectric constant of InAs as calculated from the  $\underline{k}\cdot\underline{p}$  method (————) <sup>6</sup> and as determined experimentally (-----) <sup>9</sup>. The group theoretical symmetry assignments were made with the help of the calculated isoenergy plots.
2. Reflectivity of GaSb calculated from the  $\underline{k}\cdot\underline{p}$  <sup>6</sup> and from a pseudopotential band structure <sup>11</sup>. Also, experimental reflectivity. <sup>10</sup>
3. Measured thermorefectance spectrum of GaSb <sup>15</sup> compared with the energy derivative of the spectrum of Fig. 2. <sup>16</sup>
4. Reflectivity of gray tin calculated from a first principles OPW band structure fitted with the  $\underline{k}\cdot\underline{p}$  method. <sup>19</sup> Also experimental results. <sup>20</sup>
5. Reflectivity of PbTe calculated from the APW- $\underline{k}\cdot\underline{p}$  band structure, <sup>7</sup> compared with experimental results. <sup>21</sup>
6. Absorption coefficient PbTe calculated from the APW- $\underline{k}\cdot\underline{p}$  <sup>7</sup> band structure, compared with experimental results. <sup>21, 22</sup>
7. Imaginary part of the dielectric constant of trigonal selenium for both principal directions of polarization of the electric field vector  $\underline{E}$  as calculated from the pseudopotential band structure (histograms) <sup>24</sup> and as determined experimentally. <sup>25</sup>

8. Individual density of states for gray tin, obtained from the OPW- $\underline{k}\cdot\underline{p}$  band structure.<sup>19</sup> The top of the valence band is at 0 eV. The lowest valence band is not included.
9. Conduction density of states calculate for Ge<sup>4</sup> and for GaSb<sup>6</sup> together with the function  $\epsilon_1\omega^2$  obtained from experimental data in the vacuum uv<sup>28</sup> (the horizontal scale for the  $\epsilon_1\omega^2$  curve has been shifted by 29.5 eV).
10. Contribution of the  $E_1$  gap to  $\epsilon_1$  in CdTe as measured at low temperatures by Marple and Ehrenreich<sup>33</sup> and by Cardona<sup>34</sup>. Also calculation by Kane<sup>32</sup> using the adiabatic approximation.
11. Modification in  $\epsilon_r$  and  $\epsilon_i$  introduced by the Koster-Slater exciton interaction in the neighborhood of an  $M_1$  critical point. Also, effect on the reflectivity under the assumption of an equal contribution of  $\Delta\epsilon_r$  and  $\Delta\epsilon_i$  to the reflectivity line shape.
12. Photon energy derivative spectrum of the reflectivity of HgTe in the neighborhood of the  $E_1$  and  $E_1+\Delta_1$  structure.<sup>37</sup>
13. Static dielectric constant  $\epsilon(o,\underline{q})$  obtained by Srinivasan<sup>39</sup> for Si with the Penn model compared with the interpolation formula of Eq(5) and with the results of a pseudopotential calculation by Nara<sup>40</sup> for  $\underline{q}$  along (111).

14. Experimental results for  $\epsilon_r$  in GaAs below the fundamental edge at room temperature<sup>49</sup> (circles) and fitted curve based on a model density of states.
  
15. Piezobirefringence in GaAs for an extensive stress along (100) (room temperature). The circles are experimental points. The solid line is a fit based on the model of Eq. 5.<sup>48</sup>




Figure 1




Figure 2




Figure 3






Figure 4




Figure 5




Figure 6




Figure 7




Figure 8




Figure 9




Figure 10




Figure 11






Figure 12




Figure 13




Figure 14




Figure 15